

HIGH VALUE MULTILAYER CERAMIC CAPACITORS



WAVE REFLOW


FEATURES

- The use of nickel as electrode material and plating processing improve the solderability and heat resistance characteristics. It also prevents migration and raises the level of reliability.
- Low equivalent series resistance(ESR) provides superior noise absorption characteristics.
- Compared to tantalum or aluminum electrolytic capacitors, multilayer ceramic capacitors offer a number of superior features, including:
Higher permissible ripple current values
Smaller case sizes with high rated voltage
Improved reliability due to higher insulation resistance and breakdown voltage.


APPLICATIONS

- General digital circuit
- Power supply bypass capacitors
Liquid crystal modules
Liquid crystal drive voltage lines
LSI, IC, converters(both for input and output)
- Smoothing capacitors
DC-DC converters (for both input and output)
Switching power supplies (secondary side)

ORDERING CODE



EXTERNAL DIMENSIONS/STANDARD QUANTITY



Note:
*1. Including dimension tolerance $\pm 0.15\text{mm}$ ($\pm 0.006\text{ inch}$).
*2. Including dimension tolerance $\pm 0.3\text{mm}$ ($\pm 0.012\text{ inch}$).
*3. Including dimension tolerance $\pm 0.2\text{mm}$ ($\pm 0.008\text{ inch}$).
*4. Including dimension tolerance $+0.15/-0.1\text{mm}$ ($+0.006/-0.004\text{ inch}$).

Type(EIA)	L	W	T	e	Standard quantity [pcs]	
					Paper tape	Embossed tape
□MK107 (0603)	$1.6 \pm 0.10^{+3,-4}$ (0.063 ± 0.004)	$0.8 \pm 0.10^{+3,-4}$ (0.031 ± 0.004)	$0.45 \pm 0.10^{+0.05} (0.018 \pm 0.002)$ $0.8 \pm 0.10^{+3,-4} (0.031 \pm 0.004)$	K A	0.35 ± 0.25 (0.014 ± 0.010)	4000
□MK212 (0805)	$2.0 \pm 0.10^{+1,-3}$ (0.079 ± 0.004)	$1.25 \pm 0.10^{+1,-3}$ (0.049 ± 0.004)	$0.45 \pm 0.05^{+0.05} (0.018 \pm 0.002)$ $0.85 \pm 0.10^{+0.10} (0.033 \pm 0.004)$ $1.25 \pm 0.10^{+1,-3} (0.049 \pm 0.004)$	K D G	0.5 ± 0.25 (0.020 ± 0.010)	4000
□MK316 (1206)	3.2 ± 0.15^{-3} (0.126 ± 0.006)	1.6 ± 0.15^{-3} (0.063 ± 0.006)	$0.85 \pm 0.10^{+0.10} (0.033 \pm 0.004)$ $1.25 \pm 0.10^{+0.10} (0.049 \pm 0.004)$ $1.6 \pm 0.20^{+0.20} (0.063 \pm 0.008)$	D G L	0.5 ± 0.35 (0.020 ± 0.014)	4000
□MK325 (1210)	3.2 ± 0.30 (0.126 ± 0.012)	2.5 ± 0.20^{-2} (0.098 ± 0.008)	$0.85 \pm 0.10^{+0.10} (0.033 \pm 0.004)$ $1.9 \pm 0.20^{+0.20} (0.075 \pm 0.008)$ $1.9 \pm 0.1^{+0.1} (0.075 \pm 0.008)$ $2.5 \pm 0.20^{-2} (0.098 \pm 0.008)$	D N Y M	0.6 ± 0.3 (0.024 ± 0.012)	— 2000 500(T), 1000(P)

Unit : mm (inch)

AVAILABLE CAPACITANCE RANGE

Cap [μF] [3digits]	107						212						316						325					
	TC	X7R	B/X5R	X5R	F/Y5V																			
0.1 104						A	G																	
0.15 154																								
0.22 224	A	A	A	A	A	A	G							L										
0.33 334																								
0.47 474	A	A	A	A	A	A	A	G					G	L	L	L								
0.68 684																								
1 105	A	A	A	A	A	A	A	G	G	G	G	G	L	L	L	L								
2.2 225								G	G	G	G	G					N							
3.3 335																	N	N						
4.7 475																	N	N	N	N	M			
6.8 685																								
10 106																	N	M	N	N				
22 226																	M	M	Y					
47 476																	M	M	M	N				
100 107																	M	M	M	M				

Note : Letters in the table indicate thickness.

* This catalog contains the typical specification only due to the limitation of space. When you consider purchase of our products, please check our specification. For details of each product (characteristics graph, reliability information, precautions for use, and so on), see our Web site (<http://www.ty-top.com/>) or CD catalogs.

● Low Profile Multilayer Ceramic Capacitors

Cap [μF] [3digits]	Type	107			212			316			325		
	TC	B/X5R	X5R	X7R	B/X5R	X5R	F/Y5V	B/X5R	X5R	F/Y5V	B/X5R		
	10	6.3	25	16	10	6.3	16	10	25	16	10	6.3	50
0.1	104												
0.22	224					D							
0.33	334												
0.47	474			D	D								
0.68	684												
1	105	K	K	K	K	D	D	D	D	D	D		
2.2	225		K	K	D	D	D	D	D	D	G		
3.3	335										D		
4.7	475	K	K		D	D	D	K	D	D	G	D	D
6.8	685				D	D	K		D	D	D	D	D
10	106					D	D	K		D	D	D	D
22	226					D			D	D	D	D	D
47	476								D	D			

Note : Letters in the table indicate thickness.

■ PART NUMBERS

● 107TYPE

[Temp.char. BJ:B/X5R]

Rated Voltage	Ordering code	EHS (Environmental Hazardous Substances)	Capacitance [μF]	Temperature characteristics	Dissipation factor [%] Max.	Soldering method R:Reflow soldering W:Wave soldering	Capacitance tolerance	Thickness [mm]
50V	UMK107 BJ105□A ^{*1}	RoHS	1	X5R	10	R	±10%	0.8±0.1
35V	GMK107 BJ105□A ^{*1}	RoHS	1	B/X5R	5			0.8±0.1
25V	TMK107 BJ105□K ^{*1}	RoHS	1	X5R	10			0.45±0.05
	TMK107 BJ224□A	RoHS	0.22	B/X5R	3.5			0.8±0.1
	TMK107 BJ474□A ^{*1}	RoHS	0.47	B/X5R	3.5			0.8±0.1
	TMK107 BJ105□A ^{*1}	RoHS	1	B/X5R	5			0.8±0.1
	EMK107 BJ105□K ^{*1}	RoHS	1	X5R	10			0.45±0.05
16V	EMK107 BJ224□A	RoHS	0.22	B/X5R ^{*2}	3.5	R/W	±20%	0.8±0.1
	EMK107 BJ474□A	RoHS	0.47	B/X5R ^{*2}	3.5			0.8±0.1
	EMK107 BJ105□A ^{*1}	RoHS	1	B/X5R ^{*2}	5			0.8±0.1
	EMK107 BJ225□A ^{*1}	RoHS	2.2	B/X5R	10			0.8±0.1
	EMK107 BJ105□A ^{*1}	RoHS	10	X5R	10			0.45±0.05
10V	LMK107 BJ105□K ^{*1}	RoHS	1	B/X5R	10	R	±20%	0.45±0.05
	LMK107 BJ225□K ^{*1}	RoHS	2.2	X5R	10			0.45±0.05
	LMK107 BJ475MK ^{*1,4}	RoHS	4.7	X5R	10			0.45±0.05
	LMK107 BJ224□A	RoHS	0.22	B/X5R ^{*2}	3.5			0.8±0.1
	LMK107 BJ474□A	RoHS	0.47	B/X5R ^{*2}	3.5			0.8±0.1
6.3V	LMK107 BJ105□A ^{*1}	RoHS	1	B/X5R ^{*2}	5	R/W	±10%	0.8±0.1
	LMK107 BJ225□A ^{*1}	RoHS	2.2	B/X5R	10			0.8±0.1
	LMK107 BJ475□A ^{*1}	RoHS	4.7	X5R	10			0.8±0.1
	LMK107 BJ106MA ^{*1,4}	RoHS	10	X5R	10			0.8±0.2
	JMK107 BJ105□K ^{*1}	RoHS	1	B/X5R	10			0.45±0.05
4V	JMK107 BJ225□K ^{*1}	RoHS	2.2	X5R	10	R	±20%	0.45±0.05
	JMK107 BJ475MK ^{*1}	RoHS	4.7	X5R	10			0.45±0.05
	JMK107 BJ225□A ^{*1}	RoHS	2.2	B/X5R	10			0.45±0.05
	JMK107 BJ475□A ^{*1}	RoHS	4.7	X5R	10			0.45±0.05
	JMK107 BJ106MA ^{*1}	RoHS	10	X5R	10			0.8+0.15/-0.1
4V	AMK107 BJ106MA ^{*1}	RoHS	10	X5R	10	R	±20%	0.8±0.1
	AMK107 BJ226MA ^{*1,3}	RoHS	22	X5R	10			0.8±0.2

[Temp.char. B7:X7R]

Rated Voltage	Ordering code	EHS (Environmental Hazardous Substances)	Capacitance [μF]	Temperature characteristics	Dissipation factor [%] Max.	Soldering method R:Reflow soldering W:Wave soldering	Capacitance tolerance	Thickness [mm]
16V	EMK107 B7 224□A ^{*1}	RoHS	0.22	X7R	3.5	R/W	±10%	0.8±0.1
	EMK107 B7 474□A ^{*1}	RoHS	0.47	X7R	3.5			0.8±0.1
	EMK107 B7 105□A ^{*1}	RoHS	1	X7R	5			0.8±0.1
10V	LMK107 B7 224□A	RoHS	0.22	X7R	3.5	R	±20%	0.8±0.1
	LMK107 B7 474□A	RoHS	0.47	X7R	3.5			0.8±0.1
	LMK107 B7 105□A ^{*1}	RoHS	1	X7R	5			0.8±0.1
	JMK107 B7 224□A	RoHS	0.22	X7R	3.5			0.8±0.1
	JMK107 B7 474□A	RoHS	0.47	X7R	3.5			0.8±0.1
6.3V	JMK107 B7 105□A ^{*1}	RoHS	1	X7R	5	R	±10%	0.8±0.1
	JMK107 B7 225□A ^{*1}	RoHS	2.2	X7R	3.5			0.8±0.1
	JMK107 B7 105□A ^{*1}	RoHS	10	X7R	10			0.8±0.1

[Temp.char. F:F/Y5V]

Rated Voltage	Ordering code	EHS (Environmental Hazardous Substances)	Capacitance [μF]	Temperature characteristics	Dissipation factor [%] Max.	Soldering method R:Reflow soldering W:Wave soldering	Capacitance tolerance	Thickness [mm]
50V	UMK107 F104ZA	RoHS	0.1	F/Y5V	7	R/W	±80%	0.8±0.1
	TMK107 F474ZA	RoHS	0.47	F/Y5V	7			0.8±0.1
	EMK107 F224ZA	RoHS	0.22	F/Y5V	7			0.8±0.1
16V	EMK107 F474ZA	RoHS	0.47	F/Y5V	7	R	-20%	0.8±0.1
	EMK107 F105ZA	RoHS	1	F/Y5V	16			0.8±0.1
	EMK107 F225ZA	RoHS	2.2	F/Y5V	16			0.8±0.1
10V	LMK107 F105ZA	RoHS	1	F/Y5V	16	R	±80%	0.8±0.1
	LMK107 F225ZA	RoHS	2.2	F/Y5V	16			0.8±0.1

Please specify the capacitance tolerance code. *1 1.5 times the rated voltage is applied to the chip during the high temperature loading test. *2 We may provide X7R for some items according to the individual specification. *3 The exchange of individual specification is necessary depending on the application and circuit condition. Please contact Taiyo Yuden sales channels. *4 "D" is used for the internal code.

* This catalog contains the typical specification only due to the limitation of space. When you consider purchase of our products, please check our specification. For details of each product (characteristics graph, reliability information, precautions for use, and so on), see our Web site (<http://www.ty-top.com/>) or CD catalogs.

PART NUMBERS

● 212TYPE

【Temp.char. BJ:B/X5R】

Rated Voltage	Ordering code	EHS (Environmental Hazardous Substances)	Capacitance [μ F]	Temperature characteristics	Dissipation factor [%]Max.	Soldering method R:Reflow soldering W:Wave soldering	Capacitance tolerance	Thickness [mm]
50V	UMK212 BJ104□G	RoHS	0.1	B/X5R* ²	3.5	R/W	$\pm 10\%$	1.25±0.1
	UMK212 BJ224□G* ¹	RoHS	0.22	B/X5R* ²	3.5			1.25±0.1
	UMK212 BJ474□G* ¹	RoHS	0.47	B/X5R* ²	3.5			1.25±0.1
	UMK212 BJ105□G* ¹	RoHS	1	X5R	5			1.25±0.1
25V	TMK212 BJ474□D	RoHS	0.47	B/X5R	3.5	R/W	$\pm 10\%$	0.85±0.1
	TMK212 BJ105□D	RoHS	1	B/X5R	5			0.85±0.1
	TMK212 BJ225□D* ¹	RoHS	2.2	B/X5R	5			0.85±0.1
	TMK212 BJ475□D* ^{1,4}	RoHS	4.7	X5R	10			0.85±0.1
	TMK212 BJ225□G* ¹	RoHS	2.2	B/X5R	5			1.25±0.1
	TMK212 BJ475□G* ¹	RoHS	4.7	X5R	10			1.25±0.15
16V	EMK212 BJ105□D	RoHS	1	B/X5R* ²	5	R/W	$\pm 20\%$	0.85±0.1
	EMK212 BJ225□D	RoHS	2.2	B/X5R* ²	5			0.85±0.1
	EMK212 BJ475□D* ¹	RoHS	4.7	B/X5R	10			0.85±0.1
	EMK212 BJ106□D* ^{1,4}	RoHS	10	X5R	10			1.25±0.1
	EMK212 BJ225□G	RoHS	2.2	B/X5R* ²	5			1.25±0.15
	EMK212 BJ475□G* ¹	RoHS	4.7	B/X5R* ²	5			1.25±0.15
	EMK212 BJ106□G* ¹	RoHS	10	X5R	10			1.25±0.15
	LMK212 BJ475□K* ¹	RoHS	4.7	X5R	10			0.45±0.05
10V	LMK212 BJ105□D	RoHS	1	B/X5R* ²	3.5	R	$\pm 20\%$	0.85±0.1
	LMK212 BJ225□D	RoHS	2.2	B/X5R* ²	5			0.85±0.1
	LMK212 BJ475□D	RoHS	4.7	B/X5R	10			0.85±0.1
	LMK212 BJ106□D* ¹	RoHS	10	X5R	10			0.85±0.1
	LMK212 BJ225□G	RoHS	2.2	B/X5R* ²	5			1.25±0.1
	LMK212 BJ475□G	RoHS	4.7	B/X5R* ²	5			1.25±0.15
	LMK212 BJ106□G	RoHS	10	X5R	10			1.25±0.15
	LMK212 BJ226MG* ¹	RoHS	22	X5R	10			1.25±0.2
6.3V	JMK212 BJ475□K* ¹	RoHS	4.7	X5R	10	R/W	$\pm 20\%$	0.45±0.05
	JMK212 BJ106MK* ¹	RoHS	10	X5R	10			0.45±0.05
	JMK212 BJ475□D	RoHS	4.7	X5R	10			0.85±0.1
	JMK212 BJ106□D	RoHS	10	X5R	10			0.85±0.1
	JMK212 BJ226MD* ¹	RoHS	22	X5R	10			0.85±0.1
	JMK212 BJ475□G	RoHS	4.7	B/X5R	5			1.25±0.15
	JMK212 BJ106□G	RoHS	10	X5R* ²	10			1.25±0.15
	JMK212 BJ226MG* ¹	RoHS	22	X5R	10			1.25±0.15
6.3V	JMK212 BJ476MG* ¹	RoHS	47	X5R	10			1.25±0.2

【Temp.char. B7:X7R】

Rated Voltage	Ordering code	EHS (Environmental Hazardous Substances)	Capacitance [μ F]	Temperature characteristics	Dissipation factor [%]Max.	Soldering method R:Reflow soldering W:Wave soldering	Capacitance tolerance	Thickness [mm]
50V	UMK212 B7 104□G	RoHS	0.1	X7R	3.5	R/W	$\pm 10\%$	1.25±0.1
	UMK212 B7 224□G* ¹	RoHS	0.22	X7R	3.5			1.25±0.1
	UMK212 B7 474□G* ¹	RoHS	0.47	X7R	3.5			1.25±0.1
35V	GMK212 B7 105□G* ¹	RoHS	1	X7R	3.5	R	$\pm 20\%$	1.25±0.1
25V	TMK212 B7 105□G* ¹	RoHS	1	X7R	5			1.25±0.1
16V	EMK212 B7 474□D	RoHS	0.47	X7R	3.5			0.85±0.1
	EMK212 B7 105□D	RoHS	1	X7R	5			0.85±0.1
	EMK212 B7 225□D* ¹	RoHS	2.2	X7R	5			0.85±0.1
	EMK212 B7 105□G	RoHS	1	X7R	3.5			1.25±0.1
10V	EMK212 B7 225□G* ¹	RoHS	2.2	X7R	10	R	$\pm 20\%$	1.25±0.1
	EMK212 B7 475□G* ¹	RoHS	4.7	X7R	10			1.25±0.1
	LMK212 B7 105□D	RoHS	1	X7R	3.5			0.85±0.1
	LMK212 B7 225□D	RoHS	2.2	X7R	5			0.85±0.1
10V	LMK212 B7 105□G	RoHS	1	X7R	3.5	R/W	$\pm 20\%$	1.25±0.1
	LMK212 B7 225□G	RoHS	2.2	X7R	5			1.25±0.1
	LMK212 B7 475□G* ¹	RoHS	4.7	X7R	10			1.25±0.1
	6.3V JMK212 B7 106□G* ¹	RoHS	10	X7R	10			1.25±0.15

【Temp.char. F:F/Y5V】

Rated Voltage	Ordering code	EHS (Environmental Hazardous Substances)	Capacitance [μ F]	Temperature characteristics	Dissipation factor [%]Max.	Soldering method R:Reflow soldering W:Wave soldering	Capacitance tolerance	Thickness [mm]
50V	UMK212 F224ZD	RoHS	0.22	F/Y5V	7	R/W	$\pm 10\%$	0.85±0.1
	UMK212 F474ZG	RoHS	0.47	F/Y5V	7			1.25±0.1
	UMK212 F105ZG	RoHS	1	F/Y5V	7			1.25±0.1
16V	EMK212 F225ZG	RoHS	2.2	F/Y5V	7	R	$\pm 20\%$	1.25±0.1
10V	LMK212 F225ZD	RoHS	2.2	F/Y5V	9			0.85±0.1
	LMK212 F475ZG	RoHS	4.7	F/Y5V	9			1.25±0.1
6.3V	LMK212 F106ZG	RoHS	10	F/Y5V	16			1.25±0.1
	JMK212 F475ZD	RoHS	4.7	F/Y5V	16			0.85±0.1
	JMK212 F106ZG	RoHS	10	F/Y5V	16			1.25±0.1

Please specify the capacitance tolerance code. *1 1.5 times the rated voltage is applied to the chip during the high temperature loading test. *2 We may provide X7R for some items according to the individual specification. *4 "D" is used for the internal code.

* This catalog contains the typical specification only due to the limitation of space. When you consider purchase of our products, please check our specification. For details of each product (characteristics graph, reliability information, precautions for use, and so on), see our Web site (<http://www.ty-top.com/>) or CD catalogs.

PART NUMBERS

316TYPE

【Temp.char. BJ:B/X5R】

Rated Voltage	Ordering code	EHS (Environmental Hazardous Substances)	Capacitance [μ F]	Temperature characteristics	Dissipation factor [%]Max.	Soldering method R:Reflow soldering W:Wave soldering	Capacitance tolerance	Thickness [mm]
50V	UMK316 BJ105□D* ¹	RoHS	1	B/X5R	3.5	R	$\pm 10\%$ $\pm 20\%$	0.85 ± 0.1
	UMK316 BJ225□D* ¹	RoHS	2.2	B/X5R	3.5			0.85 ± 0.1
	UMK316 BJ105□L	RoHS	1	B/X5R* ²	3.5			1.6 ± 0.2
	UMK316 BJ475□L* ¹	RoHS	4.7	X5R	10			1.6 ± 0.2
25V	TMK316 BJ105□D	RoHS	1	B/X5R	3.5	R	$\pm 10\%$ $\pm 20\%$	0.85 ± 0.1
	TMK316 BJ225□D* ¹	RoHS	2.2	B/X5R	3.5			0.85 ± 0.1
	TMK316 BJ475□D* ¹	RoHS	4.7	X5R	5			0.85 ± 0.1
	TMK316 BJ106□D* ¹	RoHS	10	X5R	10			0.85 ± 0.1
	TMK316 BJ225□L	RoHS	2.2	B/X5R* ²	3.5			1.6 ± 0.2
	TMK316 BJ475□L* ¹	RoHS	4.7	B/X5R	5			1.6 ± 0.2
16V	EMK316 BJ225□D	RoHS	2.2	B/X5R	3.5	R/W	$\pm 10\%$ $\pm 20\%$	0.85 ± 0.1
	EMK316 BJ475□D	RoHS	4.7	X5R	5			0.85 ± 0.1
	EMK316 BJ106□D* ¹	RoHS	10	X5R	10			0.85 ± 0.1
	EMK316 BJ225□L	RoHS	2.2	B/X5R* ²	3.5			1.6 ± 0.2
	EMK316 BJ475□L	RoHS	4.7	B/X5R	5			1.6 ± 0.2
	EMK316 BJ106□L* ¹	RoHS	10	B/X5R* ²	5			1.6 ± 0.2
10V	EMK316 BJ226ML* ¹	RoHS	22	B/X5R	10	R	$\pm 10\%$ $\pm 20\%$	1.6 ± 0.2
	LMK316 BJ475□D	RoHS	4.7	B/X5R	5			0.85 ± 0.1
	LMK316 BJ106□D	RoHS	10	B/X5R	10			0.85 ± 0.1
	LMK316 BJ226MD* ¹	RoHS	22	X5R	10			0.85 ± 0.1
	LMK316 BJ106□L	RoHS	10	B/X5R* ²	5			1.6 ± 0.2
	LMK316 BJ226ML* ¹	RoHS	22	B/X5R	10			1.6 ± 0.2
6.3V	LMK316 BJ476ML* ¹	RoHS	47	X5R	10	R	$\pm 10\%$ $\pm 20\%$	1.6 ± 0.2
	JMK316 BJ106□D	RoHS	10	B/X5R	10			0.85 ± 0.1
	JMK316 BJ226MD* ¹	RoHS	22	X5R	10			0.85 ± 0.1
	JMK316 BJ476MD* ¹	RoHS	47	X5R	10			0.85 ± 0.1
	JMK316 BJ106□L	RoHS	10	B/X5R* ²	5			1.6 ± 0.2
	JMK316 BJ226□L	RoHS	22	B/X5R	10			1.6 ± 0.2
4V	JMK316 BJ476ML	RoHS	47	X5R	10	R	$\pm 10\%$ $\pm 20\%$	1.6 ± 0.2
	JMK316 BJ107ML* ¹⁺³	RoHS	100	X5R	10			1.6 ± 0.2
	AMK316 BJ107ML* ¹	RoHS	100	X5R	10			1.6 ± 0.2

Please specify the capacitance tolerance code.

*1 1.5 times the rated voltage is applied to the chip during the high temperature loading test.

*2 We may provide X7R for some items according to the individual specification.

*3 The exchange of individual specification is necessary depending on the application and circuit condition. Please contact Taiyo Yuden sales channels.

【Temp.char. B7:X7R】

Rated Voltage	Ordering code	EHS (Environmental Hazardous Substances)	Capacitance [μ F]	Temperature characteristics	Dissipation factor [%]Max.	Soldering method R:Reflow soldering W:Wave soldering	Capacitance tolerance	Thickness [mm]
50V	UMK316 B7 224□L	RoHS	0.22	X7R	2.5	R/W	$\pm 10\%$ $\pm 20\%$	1.6 ± 0.2
	UMK316 B7 474□L	RoHS	0.47	X7R	3.5			1.6 ± 0.2
	UMK316 B7 105□L	RoHS	1	X7R	3.5			1.6 ± 0.2
25V	TMK316 B7 105□L	RoHS	1	X7R	3.5	R	$\pm 10\%$ $\pm 20\%$	1.6 ± 0.2
	TMK316 B7 225□L	RoHS	2.2	X7R	3.5			1.6 ± 0.2
	TMK316 B7 106□L* ⁴	RoHS	10	X7R	10			1.6 ± 0.2
16V	EMK316 B7 225□L	RoHS	2.2	X7R	3.5	R/W	$\pm 10\%$ $\pm 20\%$	1.6 ± 0.2
	EMK316 B7 106□L* ⁴	RoHS	10	X7R	10			1.6 ± 0.2
10V	LMK316 B7 225□L	RoHS	2.2	X7R	3.5	R/W	$\pm 10\%$ $\pm 20\%$	1.6 ± 0.2
	LMK316 B7 475□L	RoHS	4.7	X7R	5			1.6 ± 0.2
	LMK316 B7 106□L* ⁴	RoHS	10	X7R	10			1.6 ± 0.2
6.3V	JMK316 B7 106□L	RoHS	10	X7R	5	R	$\pm 10\%$ $\pm 20\%$	1.6 ± 0.2

Please specify the capacitance tolerance code.

*1 1.5 times the rated voltage is applied to the chip during the high temperature loading test.

*4 "D" is used for the internal code.

【Temp.char. F/Y5V】

Rated Voltage	Ordering code	EHS (Environmental Hazardous Substances)	Capacitance [μ F]	Temperature characteristics	Dissipation factor [%]Max.	Soldering method R:Reflow soldering W:Wave soldering	Capacitance tolerance	Thickness [mm]
50V	UMK316 F225ZG	RoHS	2.2	F/Y5V	7	R/W	$+80\%$ -20%	1.25 ± 0.1
35V	GMK316 F475ZG	RoHS	4.7	F/Y5V	7			1.25 ± 0.1
25V	GMK316 F106ZL	RoHS	10	F/Y5V	9			1.6 ± 0.2
16V	TMK316 F106ZL	RoHS	10	F/Y5V	9			1.6 ± 0.2
10V	LMK316 F475ZD	RoHS	4.7	F/Y5V	9			1.6 ± 0.2
6.3V	LMK316 F226ZL	RoHS	22	F/Y5V	16			0.85 ± 0.1
6.3V	JMK316 F106ZD	RoHS	10	F/Y5V	16			1.6 ± 0.2

* This catalog contains the typical specification only due to the limitation of space. When you consider purchase of our products, please check our specification. For details of each product (characteristics graph, reliability information, precautions for use, and so on), see our Web site (<http://www.ty-top.com/>) or CD catalogs.

PART NUMBERS

325TYPE

[Temp.char. BJ:B/X5R]

Rated Voltage	Ordering code	EHS (Environmental Hazardous Substances)	Capacitance [μ F]	Temperature characteristics	Dissipation factor [%]Max.	Soldering method R:Reflow soldering W:Wave soldering	Capacitance tolerance	Thickness [mm]
50V	UMK325 BJ475MM* ¹	RoHS	4.7	X5R	5	R	$\pm 20\%$	2.5±0.2
	UMK325 BJ106MM* ¹	RoHS	10	X5R	5			2.5±0.2
35V	GMK325 BJ225MN	RoHS	2.2	B/X5R	3.5	R	$\pm 20\%$	1.9±0.2
	GMK325 BJ475MN* ¹	RoHS	4.7	X5R	10			1.9±0.2
25V	GMK325 BJ106MN* ¹	RoHS	10	B/X5R	5	R	$\pm 20\%$	1.9±0.2
	TMK325 BJ106MD* ¹	RoHS	10	B/X5R	5			0.85±0.1
	TMK325 BJ335MN	RoHS	3.3	B/X5R* ²	3.5			1.9±0.2
	TMK325 BJ475MN	RoHS	4.7	B/X5R* ²	3.5			1.9±0.2
	TMK325 BJ106MN	RoHS	10	B/X5R	5			1.9±0.2
16V	TMK325 BJ106MM* ¹	RoHS	10	B/X5R* ²	3.5	R	$\pm 20\%$	2.5±0.2
	EMK325 BJ106MD* ¹	RoHS	10	B/X5R	5			0.85±0.1
	EMK325 BJ226MD* ¹	RoHS	22	B/X5R	10			0.85±0.1
	EMK325 BJ475MN	RoHS	4.7	B/X5R* ²	3.5			1.9±0.2
	EMK325 BJ106MN	RoHS	10	B/X5R	3.5			1.9±0.2
	EMK325 BJ226MM* ¹	RoHS	22	B/X5R	5			2.5±0.2
10V	EMK325 BJ476MM* ¹	RoHS	47	X5R	10	R	$\pm 20\%$	2.5±0.2
	LMK325 BJ335MD	RoHS	3.3	B/X5R	3.5			0.85±0.1
	LMK325 BJ475MD	RoHS	4.7	B/X5R	5			0.85±0.1
	LMK325 BJ106MD* ¹	RoHS	10	B/X5R	5			0.85±0.1
	LMK325 BJ226MY* ¹	RoHS	22	B/X5R	5			1.9+0.1/-0.2
	LMK325 BJ106MN	RoHS	10	B/X5R* ²	3.5			1.9±0.2
	LMK325 BJ226MM	RoHS	22	B/X5R	5			2.5±0.2
6.3V	LMK325 BJ476MM* ¹	RoHS	47	X5R	10	R	$\pm 20\%$	2.5±0.2
	LMK325 BJ107MM* ¹	RoHS	100	X5R	10			2.5±0.3
	JMK325 BJ226MY	RoHS	22	B/X5R	5			1.9+0.1/-0.2
	JMK325 BJ107MY* ¹	RoHS	100	X5R	10			1.9+0.1/-0.2
	JMK325 BJ476MN* ¹	RoHS	47	X5R	10			1.9±0.2
6.3V	JMK325 BJ476MM* ¹	RoHS	47	X5R	10	R	$\pm 20\%$	2.5±0.2
	JMK325 BJ107MM* ¹	RoHS	100	X5R	10			2.5±0.3

Please specify the capacitance tolerance code.

*1 1.5 times the rated voltage is applied to the chip during the high temperature loading test.

*2 We may provide X7R for some items according to the individual specification.

[Temp.char. B7:X7R]

Rated Voltage	Ordering code	EHS (Environmental Hazardous Substances)	Capacitance [μ F]	Temperature characteristics	Dissipation factor [%]Max.	Soldering method R:Reflow soldering W:Wave soldering	Capacitance tolerance	Thickness [mm]
25V	TMK325 B7 335MN	RoHS	3.3	X7R	3.5	R	$\pm 20\%$	1.9±0.2
	TMK325 B7 475MN* ¹	RoHS	4.7	X7R	3.5			1.9±0.2
16V	EMK325 B7 475MN	RoHS	4.7	X7R	3.5	R	$\pm 20\%$	1.9±0.2
	LMK325 B7 106MN	RoHS	10	X7R	3.5			1.9±0.2

Please specify the capacitance tolerance code.

*1 1.5 times the rated voltage is applied to the chip during the high temperature loading test.

[Temp.char. F:F/Y5V]


Rated Voltage	Ordering code	EHS (Environmental Hazardous Substances)	Capacitance [μ F]	Temperature characteristics	Dissipation factor [%]Max.	Soldering method R:Reflow soldering W:Wave soldering	Capacitance tolerance	Thickness [mm]
16V	EMK325 F226ZN	RoHS	22	F/Y5V	16	R	$+80\% -20\%$	1.9±0.2
	LMK325 F226ZN	RoHS	22	F/Y5V	16			1.9±0.2
	JMK325 F476ZN	RoHS	47	F/Y5V	16			1.9±0.2

* This catalog contains the typical specification only due to the limitation of space. When you consider purchase of our products, please check our specification. For details of each product (characteristics graph, reliability information, precautions for use, and so on), see our Web site (<http://www.ty-top.com/>) or CD catalogs.

ELECTRICAL CHARACTERISTICS

Example of Impedance ESR vs. Frequency characteristics

Taiyo Yuden multilayer ceramic capacitor



* This catalog contains the typical specification only due to the limitation of space. When you consider purchase of our products, please check our specification. For details of each product (characteristics graph, reliability information, precautions for use, and so on), see our Web site (<http://www.ty-top.com/>) or CD catalogs.